

## FloTek™ 1225

### Normal Setting Water Reducing Admixture

#### General Description

FloTek™ 1225 is a normal setting water-reducing admixture for concrete. It is designed to facilitate the placing and finishing of concrete while providing control over set time. FloTek 1225 is also a set retarding admixture beneficial during hot weather concreting operations when control of setting time and maintenance of placeable consistency are essential. FloTek 1225 can be used as a cost effective water reducing admixture for production of conventional slump concrete.

#### Features/Advantages

- Provides variable control of setting time based on dosage rate and improves quality of concrete by decreasing water-cement ratio while maintaining slump life during extended mixing times.
- Increases compressive and flexural strengths.
- Reduces cracking, shrinkage, surface bleeding and segregation.
- Resists damage caused by freezing and thawing and aids in preventing cold joints and reduces thermal cracking in mass pour concrete.

#### How to Use/Dosage

Dosage: Rates will vary depending on the materials used, ambient conditions and the requirements of a specific project. For best results, each admixture must be introduced separately into the concrete mix. FloTek 1225 is normally added to the concrete mix at the following dosage rates as a function of temperature.

Dosage per 100 lbs. of cement:

65 - 75°F - 3.5 fl oz.

75 - 85°F - 4 fl oz.

85 - 90°F - 4.5 fl oz.

90 - 100°F - 5 fl oz.

Due to variations in concrete materials, job site conditions and applications, dosages outside of the recommended range may be required. In such cases, contact your local Riteks Construction Chemical Representative.

Note: FloTek 1225 does not contain calcium chloride or any chloride-based components and is non-corrosive to reinforced, galvanized floor/roof systems or prestressing steel.

#### Specifications

Conforms to: ASTM C 494 Types A, B & D

#### Compatibility

All types Portland cement, class C and F fly ash, silica fume, fibers, approved air entraining, water reducing and superplasticizing admixtures. FloTek 1225 can be used in white, colored and architectural concrete.

#### Health & Environmental Data

Please refer to the Safety Data Sheet for complete health, safety and environmental information.

#### Packaging / Shelf Life

55 gallon drum • Totes • Bulk deliveries

Store between 32° F & 100° F. Protect from freezing. Product should be used within 12 months of delivery.

For additional information on this product, please contact your Riteks Sales Representative.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



415 Interchange St. McKinney, TX 75071

Ph: 972.529.1118 Toll free: 866.288.5121

[www.riteks.com](http://www.riteks.com)