

## NexCrete™ 1310

### Mid-Range Water Reducing Admixture

#### General Description

Riteks NexCrete™ 1310 is an economical mid-range water-reducing (MRWR) admixture based on polycarboxylate technology. NexCrete 1310 is especially suitable for ready mix, pre-cast, Self-Consolidating Concrete (SCC) and mix designs containing fly ash or pozzolonic material. NexCrete 1310 is ready-to-use and provides excellent early compressive strength, faster setting strengths & fluidity in plastic hardened concrete.

#### Features/Advantages

- Significant water reduction
- Increased workability
- Reduced labor required for placement
- Increased long term strength and reduced permeability
- Excellent early strength development
- Mix design stability

#### How to Use/Dosage

Mixing: NexCrete 1310 can be added with the initial batch water but delayed addition will generally result in optimum water reduction. Dosage rates will vary depending on the materials used, ambient conditions and the requirements of a specific project.

Dosage Rate: 3 to 18 fl. oz. per 100 lbs of cementitious material. Due to variations in concrete materials, job site conditions and applications, dosages outside of the recommended range may be required. In such cases, contact your local Riteks Construction Chemical Representative.

Note: NexCrete 1310 does not contain calcium chloride or any chloride-based components and is non-corrosive to reinforced, galvanized floor/roof systems or prestressing steel. Do not use with admixtures containing beta-naphthalene sulfonate.

#### Health & Environmental Data

Please refer to the Safety Data Sheet for complete health, safety and environmental information.

#### Packaging / Shelf Life

5 gallon pail · 55 gallon drum  
Totes · Bulk deliveries

Store between 32° F and 100° F.  
Product should be used within  
12 months of delivery.

For additional information on this product, please contact your Riteks Sales Representative.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



415 Interchange St. McKinney, TX 75071  
Ph: 972.529.1118 Toll free: 866.288.5121  
[www.riteks.com](http://www.riteks.com)