

SYAD™ 75 *Retarding Admixture*

General Description

SYAD™ 75 is a retarding admixture recommended for all concrete where extended setting characteristics, particularly in hot weather are desired. SYAD 75 delays time of set to accommodate long haul times, or facilitate placement and finishing during hot weather concreting.

Primary Applications

SYAD 75 was designed to be used where an economical and effective retarding is required to offset the accelerating effects of high ambient temperature concreting. SYAD 75 will delay initial set times allowing proper placement and finishing without cold joints in hot weather conditions.

Features/Advantages

- Delays setting characteristics
- Improves workability and finishability
- Excellent retarding properties

How to Use / Dosage

Mixing: SYAD 75 should not come into contact with dry cement or other admixtures until mixed. Dosage: Rates will vary depending on the materials used, ambient conditions and the requirements of a specific project.

For best results, add SYAD 75 to the water and aggregate mix at between 1.5-3 fl. oz of 100 lbs. of cementitious materials. Due to variations in concrete materials, job site conditions and applications, dosages outside of the recommended range may be required. In such cases, contact your local Riteks Construction Chemical Representative.

Note: SYAD 75 does not contain calcium chloride or any chloride-based components and is non-corrosive to reinforced, galvanized floor/roof systems or prestressing steel.

Specifications

Conforms to: ASTM C 494 Type B

Health & Environmental Data

Please refer to the Safety Data Sheet for complete health, safety and environmental information.

Packaging / Shelf Life

55 gallon drum • Totes • Bulk deliveries

Store between 32° F & 100° F. Product should be used within 12 months of delivery.

For additional information on this product, please contact your Riteks Sales Representative.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



415 Interchange St. McKinney, TX 75071

Ph: 972.529.1118 Toll free: 866.288.5121

www.riteks.com