

Riteks™ WATERPEL-S25

Superior Integral Water Repellant for Masonry Products

General Description

WATERPEL-S25 is a unique multi-component, liquid water repellant admixture based on a new technology that exhibits superior performance versus conventional water repellents.

WATERPEL-S25 provides long-lasting resistance to water penetration by reacting to form a very effective water resistant network throughout manufactured concrete products.

WATERPEL-S25, when incorporated properly in concrete masonry units, will provide superior water repellency performance based on NCMA TEK 19, spray bar test and ASTM E514 wind driven rain test.

Features/Advantages

- Less maintenance and moisture damage due to integral water repellency
- Inhibits water transmission through hardened cast-in-place concrete
- Less penetration at the surface reduces coats of paint required
- Improves color trueness and consistency
- Reduces mildew and mold growth
- Enhances texture
- Improves aesthetics and appearance
- Controls and reduces efflorescence

Dosage

WATERPEL-S25 is recommended for use at the following dosages:

- 4 -20 ozs./cwt.- For Water Repellency (261 - 1305 ml/100kg)
- 2 -20 ozs./cwt.- For Efflorescence Control (130 - 1305 ml/100kg)

Because local job conditions vary and optimum dosages need to be determined, contact your local Riteks technical service representative for further assistance to ensure proper water repellant system performance.

WATERPEL-S25 should be added after initial wetting of the aggregates and cement and after a minimum of 75% of the total mix water has been added to the mix. Once added to the mix, allow a minimum of 90 seconds mix time to insure WATERPEL-S25 has been properly dispersed throughout the mix.

Use of ES-2000 or any quality Riteks plasticizer is recommended to brighten colors, lower permeability and increase compressive strength.

Applications

WATERPEL-S25 is an integral water-repellant admixture system for use in:

- Concrete block (normal, medium, and lightweight)
- Precast and Prestressed Concrete
- Segmental retaining wall units
- Concrete roofing tile
- Pavers

Packaging

55 gal Drum | 275 gal Totes

Shelf Life

12 months in original unopened container.



Scan to Request
a Sample
[281.569.3500](tel:281.569.3500)
service@riteks.com



Riteks™ WATERPEL-S25

Superior Integral Water Repellant for Masonry Products

Technical Note

Flashing and weep hole design details are available upon request.

Efflorescence occurs when excess calcium salts become soluble again from moisture in the environment around the concrete or masonry unit. External sources of moisture can be humidity, rainfall, condensation, or snow etc.

When these salts become soluble, they migrate to the surface during the evaporation process, consequently, staining the surface.

WATERPEL-S25, as mentioned earlier, effectively reduces moisture from penetrating the surface and may be helpful in stopping salts from becoming soluble and migrating to the surface.

It is important to point out that the addition of **WATERPEL-S25** alone, will not guarantee the control of efflorescence.

Riteks cannot be responsible for incorrect use of **WATERPEL-S25**.

Riteks mortar additive must be used in the masonry mortar in order to achieve a moisture penetration resistant wall system. Failure to incorporate the mortar additive will compromise water repellency performance of the masonry structure.

Storage

WATERPEL-S25 may freeze at temperatures below 40F (4 C).

Freezing will harm this material and render it unusable, so precautions should be taken to protect it from freezing. If it should freeze, it will no longer be effective in the masonry units.

Also, **WATERPEL-S25** should be stored in sealed containers where temperatures don't exceed 105 F (40 C).

Compatibility

WATERPEL-S25 is fully effective and compatible in masonry concrete containing all types of Portland cement, class C and F fly ash, silica fume, calcium chloride, fibers and approved water-reducing, accelerating and retarding admixtures.

WATERPEL-S25 can be used in white, colored, and architectural concrete.

Health And Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations

Precautions

WATERPEL-S25 will not correct building design flaws, out of spec materials, mix proportion errors, incorrect manufacturing procedures, or unorthodox construction practices.

Proper block manufacturing procedures, mixing, and proportioning of mixes must be incorporated.



Scan to Request
a Sample

281.569.3500
service@riteks.com

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. RITEKS shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. RITEKS, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.

