

## Microfume 102DM

### General Description

Microfume 102 DM is densified, constant pH, amorphous light grey silicon oxide powder. Microfume 102 DM improves the mechanical properties (compressive strength) and durability (via permeability decrease). Microfume 102 DM can be used as an extender for lightweight cements and a compressive-strength enhancer for low-temperature, lightweight cements.

### Applications

Microfume 102 DM improves the mechanical properties (compressive strength, creep, modulus of rupture) and durability (via permeability decrease).

### Packaging/Storage

Bulk super-sack, 25 or 50 lb. bags, other packaging options are available on request. Store in a dry area protected from moisture. Once bags are opened they must be sealed until all material is used.

### Health and Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations.

### Production Site:

Burnsville, MS (USA).

Quality Control: Complies with ISO

9001:2008 Environment: Complies with the ISO 14001:2000

<b>Physical and chemical characteristics:</b>			
<b>Analysis**</b>	<b>Typical</b>	<b>Limits</b>	
		<b>Min</b>	<b>Max</b>
SiO <sub>2</sub> (%)	97.0	95.5	98.7
Free C (%)	1.1	0.6	2.2
Free Si (%)	0.12	0.1	0.16
Total CaO (%)	0.42	.19	.82
SO <sub>3</sub> (%)	0.01	0.008	.09
Na <sub>2</sub> O (%)	0.06	0.1	0.25
K <sub>2</sub> O (%)	0.38	0.35	0.6
Cl <sup>-</sup> (ppm)	15	10	20
Al <sub>2</sub> O <sub>3</sub> (%)	< 0.09	<0.07	0.15
Fe <sub>2</sub> O <sub>3</sub> (%)	< 0.03***	< 0.01***	< 0.1***
MgO (%)	0.11	< 0.1	0.25
H <sub>2</sub> O (%)	0.29	0.1	1
PH	7.6	6.75	8
Loss on Ignition (at 950°C during 1h) (%)	1.15	1	2.5
Specific surface (BET) (m <sup>2</sup> /g)	20	18	22.5
Bulk density (lb/ft <sup>3</sup> )	42	39	46
> 45 urn (%)	1.9	1.1	2.5
Brightness L*	47	45	50

\*\* % by weight of dry mass. \*\*\* Lower limit of detection.

*Typical properties given do not constitute a supply specification.*

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Ritek's shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Ritek's, Inc. believes to be reliable. Ritek's, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.