

## NexCrete™ 1610

### Mid-Range Water Reducing Admixture

#### General Description

Riteks NexCrete™ 1610 is a normal setting multi-range water-reducing admixture for concrete utilizing polycarboxylate technology. It is designed to facilitate the placing and finishing of ready mixed concrete that is highly flowable and workable for extended periods of time with normal setting characteristics. By varying the dosage rate, Nexcrete 1610 can be used as a normal, mid-range and high-range water-reducing admixture

#### Features/Advantages

- Improves the quality of concrete by decreasing water-cementitious ratio
- Increases high early and ultimate strengths both compressive and flexural
- High durability and increased density
- Reduces damage caused by freezing and thawing
- Reduces water content needed for a given workability (12-40%)
- Reduces surface bleeding, cracking, creep, and shrinkage
- Reduces segregation and increase cohesiveness
- Improves finishability, workability of concrete and pumpability of concrete
- Maintains slump life during extended mixing times
- Plasticity range of 8 to 11 inches
- Improves bond strength to the steel
- Reduces permeability and salt penetration

#### How to Use / Dosage

NexCrete 1610 should be added with the initial mixing water or incorporated with the final water at the end of the batch sequence. It is not unusual to experience significantly lower air entrainment dosage requirements (50-75%) when compared to conventional high-range water reducers.

- Dosage to meet ASTM C 494 Type F applications: 7 to 20 fl. oz. per 100 lbs.
- Dosage to meet: ASTM C 494 Type A applications: up to 3 fl. oz. per 100 lbs.
- Dosage to meet mid-range applications: 3 to 6 fl. oz. per 100 lbs.

Due to variations in concrete materials, job site conditions and applications, dosages outside of the recommended range may be required. In such cases, contact your local Riteks Construction Chemical Representative. Note: NexCrete 1610 does not contain calcium chloride or any chloride-based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.

#### Specifications

Conforms to:

- ASTM C 494 Types A and F
- AASHTO M 194 Types A and F
- CRD C 87 Types A and F
- All other Federal & State specifications

#### Compatibilites

All types Portland cement, class C & F, fly ash, silica fume, fibers, approved air entraining, and water-reducing admixtures. Can be used in white, colored, and architectural concrete. For best results, each admixture must be introduced separately into the concrete mix.

#### Packaging/Storage

5 gallon pail • 55 gallon drum  
Totes • Bulk deliveries

Store between 32° F & 100° F. Product should be used within 18 months of delivery.

#### Health and Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations.



Headquarters:

11917 Cutten Road Houston, TX 77066  
Ph: [281] 569-3500 • Fax: [281] 569-3508  
[www.riteks.com](http://www.riteks.com)

Dallas Plant :

415 Interchange Street McKinney, TX 75071