

Riteks RCR-200

Mid Temperature Retarder

General Description

Riteks RCR-200 is a sodium lignosulfonate cement retarder that can be used to retard all API classes of cement as well as Pozz-Cement. RCR-200 retarder is effective in wells with bottom-hole circulating temperatures (BHCTs) up to 220°F (104.4°C). It can also withstand static temperatures up to 260°F (126.7°C). RCR-200 is particularly useful in cements containing high gel percentages, and increased concentrations of RCR-200 enhance the predictability of cement thickening times.

Features and Benefits

Riteks RCR-200 can provide the following benefits:

- Increased concentrations of RCR-200 enhance the predictability of cement thickening times
- Improved slurry displacement rates at steady pressures
- Provides early cement-strength development
- Aid in extending a slurry's temperature range and yield a smoother, more uniform slurry.
- Decreases the danger of over-retarded slurries at the top of a long cement column.
- Helps displace slurries at high rates while maintaining formation pressure.

Applications

Riteks RCR-200 is effective in wells with bottom-hole circulating temperatures (BHCTs) from 100°F (37.8°C) up to 220°F (104.4°C). It can also withstand static temperatures up to 260°F (126.7°C). RCR-200 is very consistent & decreases the danger of over-retarded slurries at the top of a long cement column.

Typical Properties

- Color: Dark Brown
- Moisture, %: <8.0%
- % Solids: 93 – 98%
- pH: 3-5
- Specific Gravity: 1.23 – 1.29
- Absolute Volume: 0.0952
- Bulk Density: 25 lb/ft³

Typical properties given do not constitute a supply specification.

Packaging/Storage

Available in 55.12# (25kg) paper bags & 1322.77# (600kg) supersacks

Store in a cool, dry, well-ventilated area. Under dry conditions, powder products remain stable for several years.

Health and Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection there with. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



11917 Cutten Road Houston, TX 77066
Ph: [281] 569-3500 • Fax: [281] 569-3508
www.riteks.com