

Slump Retain 240

Slump Retaining Admixture for Concrete

General Description

Riteks Slump Retain 240 is a revolutionary new technology based on significant advances in the admixture industry. When used as part of an admixture system, it provides slump retention without retardation. Slump Retain 240 gives the concrete producer the ability to immediately create the ideal admixture system for fluctuating regional raw materials, environmental conditions and project requirements.

Primary Applications

- Concrete with varying slump requirements
- Concrete mixtures utilizing supplementary cementitious materials
- Concrete where increased stability, durability and high flowability are required
- Concrete requiring the production of self consolidating concrete (SCC) mixtures

Features/Advantages

- Workability retention without retardation
- Flexible levels of workability retention by adjusting dosage
- Improved early and late age compressive strengths
- Promotes greater consistency of concrete workability at the jobsite
- Promotes consistency in compressive strengths via minimized jobsite addition of water
- Minimizes re-dosing of high range water reducing admixture at the jobsite
- Consistent air entrainment
- Fewer rejected loads and better customer satisfaction due to consistent quality of concrete

How to Use / Dosage

Recommended Dosage Rate: 2 to 12 fl. oz. per 100 lbs. of cementitious material. It can be added with the initial batch water or as a delayed addition.

Note: Slump Retain 240 does not contain calcium chloride or any chloride-based components and is non-corrosive to reinforced, galvanized floor/roof systems or prestressing steel. Do not use with admixtures containing beta-naphthalene sulfonate.

Conforms to:

- ASTM C 494 Type A
- ASTM C 494 Type S
- ASTM C 494M Type A
- ASTM C 494M Type S

Compatibility

Slump Retain 240 is compatible with most admixtures used in the production of quality concrete including normal, mid-range and high-range water reducing admixtures, air entrainers, accelerators, retarders, extended set control admixtures, corrosion inhibitors and shrinkage reducers. Slump Retain 240 is not recommended for use with any Poly Naphthalene Sulfonate based admixtures.

Packaging/Storage

5 gallon pail • 55 gallon drum
Totes • Bulk deliveries

Store between 32° F & 100° F. Product should be used within 12 months of delivery.

Health and Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



Headquarters:

11917 Cutten Road Houston, TX 77066
Ph: [281] 569-3500 • Fax: [281] 569-3508
www.riteks.com

Dallas Plant :

415 Interchange Street McKinney, TX 75071