

Riteks CSE-5

High-Quality Pozzolanic Additive for Concrete

General Description

Riteks CSE-5 is high-reactivity metakaolin pozzolan produced by thermal activation of high purity kaolin clay within a specific temperature range that meets or exceeds all of the specifications of ASTM C-618 Class N pozzolans. Riteks CSE-5 reacts with free lime produced during hydration of cement and produces additional cementitious material.

Unlike other pozzolanic materials, CSE-5 was developed to maintain high reactivity, ultrafine particle size distribution and product consistency.

Applications

Riteks CSE-5 is designed for use in a range of cementitious applications, including: downhole cement, manufactured concrete products (MCP) and plaster. The pozzolanic properties of CSE-5 yield superior strength and durability while simultaneously protecting against chemical attack, specifically efflorescence and Alkali-Silica Reaction (ASR). CSE-5 has good synergy with silica fume, while being used at reduced loading levels to provide high early compressive strength development in low density slurries. Additional benefits include extender properties & free water control.

Loading Levels

Recommended loading levels for CSE-5 are 3-5% bwoc.

Typical Properties

Physical Form: Highly pulverized powder
Screen Residue, 325 Mesh (%): 3.5
Free Moisture (%), measured at 105°C: 1.1
pH (20% solids): 4.8
Median Particle Size, Sedigraph (μm): 1.3
Specific Gravity: ~2.6
Absolute Volume: ~0.0461
Bulk Density, Loose lb/ft³ (kg/m³): 25.4 / 406.9
Bulk Density, Tamped lb/ft³ (kg/m³): 32.3 / 517.4

Typical properties given do not constitute a supply specification

Packaging/Storage

Under dry conditions, powder products remain stable for several years.

Available in 50 lb. net weight multi-wall kraft bags, 2000 lb. Supersacks & bulk.

Health and Environmental Data

Before handling or using this product please refer to the Safety Data Sheet for complete health, safety and environmental information. Dispose of waste in accordance with local, state and federal regulations.

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, RITEKS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Riteks shall have no other liability with respect thereto. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that Riteks, Inc. believes to be reliable. Riteks, Inc. makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgment as to the appropriateness of its use and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.